

KyronMAX™ S-8230

PRODUCT TECHNICAL DATA SHEET

MECHANICAL	Test Method	English		Metric	
		Typical Value	Unit	Typical Value	Unit
Specific Density	ASTM D792	1.43	g/cm ³	1.43	g/cm ³
Tensile Strength	ASTM D638	39,000	psi	269	MPa
Tensile Modulus of Elasticity	ASTM D638	4,300	ksi	30	GPa
Tensile Elongation	ASTM D638	1.4	%	1.4	%
Flexural Strength	ASTM D790	55,000	psi	379	MPa
Flexural Modulus of Elasticity	ASTM D790	3,900	ksi	27	GPa
Compressive Strength	ASTM D695	41,300	psi	285	MPa
Compressive Modulus of Elasticity	ASTM D695	1,010	ksi	7	GPa
Notched Izod Impact	ASTM D256	1.3	ft-lb/in	69	J/m
Unnotched Izod Impact	ASTM D4812	10	ft-lb/in	534	J/m
THERMAL	Test Method	Typical Value	Unit	Typical Value	Unit
Glass Transition (T _g)	ASTM D3418	210	°F	99	°C
Melting Point	ASTM D3418	539	°F	282	°C
ELECTRICAL	Test Method	Typical Value	Unit	Typical Value	Unit
Flammability	UL 94 ¹	V-0		V-0	
CHEMICAL	Test Method	Typical Value	Unit	Typical Value	Unit
Moisture, 24 hours	ASTM D570	0.05	% by wt	0.05	% by wt
OTHER	Test Method	Typical Value	Unit	Typical Value	Unit
Linear Mold Shrinkage, Flow		0.00 – 0.20	%	0.00 – 0.20	%
Linear Mold Shrinkage, Transverse		0.45 – 0.65	%	0.45 – 0.65	%

USA – Arizona

257 East Alamo Drive
Chandler, AZ 85225 USA
Tel: 480.926.8100
Fax: 480.497.1530
KyronMAX@mcam.com

USA – Illinois

1840 Enterprise Court
Libertyville, IL 60048 USA
Tel: 847.367.0110
Fax: 847.367.0566

Asia – Thailand/Singapore

Eastern Seaboard Industrial Estate
Rayong 64/103, Moo 4, T. Pluakdaeng
A. Pluakdaeng, Rayong 21140 Thailand
Tel: +66 33 659 141
Fax: 847.367.0566

<https://mcam.com>

ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, Mitsubishi Chemical Advanced Materials (MCAM) MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING MCAM MATERIALS, PRODUCTS, RECOMMENDATIONS OR ADVICE. MCAM AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS OR PRODUCTS DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of MCAM materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating MCAM materials or products will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of MCAM Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by MCAM.

¹Does not represent actual testing conducted by MCAM but is an estimated rating based on available data. The UL 94 Test is a laboratory test and does not relate to actual fire hazard.